

PAIN T SYSTEM NO. 5

SURFACE PREPARATION -PRESSURE WASH SURFACE TO BE PAINTED

OPTIMAL APPLICATION CONDITIONS

AMBIENT TEMPERATURE BETWEEN 55 AND 75 DEGREES F.

HUMIDITY BELOW 60 PERCENT

IF OUTSIDE THESE LIMITS, REQUEST PERMISSION TO APPLY PAINT FROM COA INSPECTOR OR SERVICES DURING CONSTRUCTION ENGINEER

APPLY (SPRAY) FIRST COAT

APPLY (SPRAY) SECOND COAT EITHER WITHIN TWO HOURS OR MORE THAN 48 HOURS AFTER APPLYING FIRST COAT.

PRODUCT

KRYLON SPRAY PAINT

FUSION ALL-IN-ONE

PAINT PLUS PRIMER

COLORS

POTABLE WATER - GLOSS PATRIOTIC BLUE

WASTEWATER - GLOSSY SPRING GRASS

RECLAIMED - GLOSSY ICY GRAPE

307

PAINT SYSTEM NO. 5
NTS

